
VAUTID 35

Tubular wire Hardfacing material for continuous casting rollers











| Specification | Tubular wire electrode DIN EN 14700 T Fe7 cpt | | |
|-----------------------------------|--|--|--|
| Material type Alloy components | Hardfacing material on iron base with Chromium, Nickel and Molybdenum additions $\mbox{\rm Cr}-\mbox{\rm Ni}-\mbox{\rm Mo}$ | | |
| Welding deposit characteristics | VAUTID 35 produces a crack-free, martensitic stainless steel weld deposit. Perfectly suited for parts exposed to heat (oxidation), corrosion, impact and medium wear. The weld material can be machined and forged | | |
| Weld deposit properties | Hardness of pure welding deposit (acc. DIN 32525-4): approx. 20 HRC Hardness 1. Layer on S235JR (1.0037): approx. 42 - 47 HRC | | |
| Recommended applications | Typically applications are build-up layers for continuous casting rollers, valve seats , gate walves and metal to metal applications in general | | |
| Standard sizes | Tubular wires: Diameter 2,4 / 2,8 mm Packing: Reels of approx. 25 kg, Drums of approx. 250 kg | | |

^{*} subject to common industrial fluctuations

Welding instructions for tubular wires:

VAUTID 35 tubular wires are welded open-arc without inert gas on the +pole. In order to prevent slag-flow sagging wire-guiding should be preferred. Both the weave bead and the stinger bead techniques can be used. Several layers can be welded

| Diameter (mm) | Current (A) | Voltage (V) | Stick out (mm) |
|------------------|----------------|-------------|-------------------|
| 1,6 | 160 – 280 | 24 – 27 | 20 – 35 |
| 2,0 | 180 – 310 | 25 – 28 | 24 – 45 |
| 2,4 | 220 – 350 | 26 – 29 | 24 – 45 |
| 2,8 | 270 – 430 | 27 – 30 | 30 – 50 |
| 3,2 | 290 – 470 | 28 – 30 | 30 - 55 |

Welding positions (EN ISO 6947): PA, PB

This data sheet corresponds to the present state of production (October 2016) and can be changed anytime.